

EUROPERL[®] 50

IMERYS FILTRATION EMEA

Sales Office

2 Place E. Bouillères – BP 33662
31036 Toulouse Cedex 1 – France
T +33 561 50 20 20
F +33 561 40 06 23

Production Site

Alzaia Trento 6
20094 Corsico (MI) - Italy
Tel: +39 02 451 74200
Fax: +39 02 440 74224

PERLITE FILTER AID

PRODUCT

Production site	Milan, Italy
Product type	Perlite

TYPICAL PHYSICAL PROPERTIES

Physical form	Dry Powder
Colour	White
Permeability (Da)	0.30
Cake Density (g/l)	309
Moisture (% by weight as shipped)	1
Floaters (% by volume)	Trace

Typical Particle Size (%)

Retained on 74 microns (200 mesh)	10
Retained on 44 microns (325 mesh)	25

TYPICAL CHEMICAL PROPERTIES (% by weight unless otherwise stated)

SiO ₂	72
Al ₂ O ₃	14
Fe ₂ O ₃	0.7
TiO ₂	0.1
CaO	0.3
MgO	0.1
Na ₂ O	4
K ₂ O	8.8

Notice: Although the data listed are typical, they are not production specifications. The supplier provides the data in good faith, however it makes no warranty or representation of any kind, express or implied, regarding the information given or product described including any warranty of suitability for a particular purpose.

DAT721P – February 2018 – Fourth edition

